

A partner within every step you make

Technical Data Sheet

• PPTENE™ RN4332



Polymer Plus Technologies Ltd.
P.O. Box 1938 Dammam 31441,
Dammam – Kingdom of Saudi Arabia.
Tel: +966 3 8128668
Fax: +966 3 8128667

sales@polymerplus.com.sa

Product Description

RN4332 is an injection moulding grade Linear Low Density Polyethylene copolymer with narrow molecular weight distribution. It has been designed to have excellent low temperature toughness, stress crack resistance and gloss.

RN4332 is available in its natural powder form.

RN4332

LLDPE
Injection Moulding Grade

Melt Flow Index: 20.0 g/10 min
Density: 0.924 g/cm³

Typical applications
Masterbatch

Physical Characteristics¹

Characteristics	Value	Unit	Test Method
Melt Flow Index (MFI)	20.0	g/10min	ASTM D 1238
Density	0.924	g/cm ³	ASTM D 1505
Vicat Softening Point	94	°C	ASTM D 1525
Brittleness Temperature	<-75	°C	ASTM D 746
Secant Modulus @ 1% Elongation	315	MPa	ASTM D 638
Tensile Strength @ Yield	12	MPa	ASTM D 638
Tensile Strength @ Break	8.5	MPa	ASTM D 638
Tensile Elongation @ Break	450	%	ASTM D 638
Izod Impact (notched)	540	J/m	ASTM D 256
Hardness (Shore D)	55	-	ASTM D 2240
ESCR (100% Igepal) (F ₅₀)	24	h	ASTM D 1693A

¹ Data values shown are average values for the base resin and should not be used for specification limits.

Polymer Plus Technologies Ltd. makes no representations or warranties and there are no conditions with respect to the accuracy, reliability, or application of the information herein, its products or the safety or suitability thereof, or results obtained, whether expressed or implied including, without limitation, any implied warranty or merchantability or fitness for a particular purpose. Buyers and users must determine the results to be obtained from the application of the information herein and the safety and suitability of Polymer Plus Technologies Ltd. products for their own purposes, and assume all risk, responsibility, and liability for all injuries, losses, or damages arising from the application of the information herein or use of Polymer Plus Technologies Ltd. products, whether or not occasioned by Polymer Plus Technologies Ltd. negligence or based on strict product liability. Polymer Plus Technologies Ltd. neither assumes nor authorizes any person to assume for it any liability in connection with the use of information herein or its products.